

TECTYL 506

Description

TECTYL 506 is a solvent cutback, wax base, corrosion preventive compound. The dry film is firm, amber, waxy and translucent. TECTYL 506 is excellent for long term

Protection of metallic surfaces against corrosion in either indoor or outdoor exposure and during domestic and international shipments.

Laboratory Data

Typical Properties

	<u>English</u>	<u>Metric</u>
Flash, PMCC, Minimum	100°F	38°C
Specific Gravity @ 60°F(15.6°C)	0.88	0.88
Recommended Dry Film Thickness	1.3 mils	32.5 microns
Theoretical Coverage	630 sq. ft./ U.S gallon	15.4 sq. meters/ liter
Non Volatile % by Weight	53-57	-
Approximate Air Dry Time @ 77°F(25°C)	1hour	1hour
High Temperature Flow Point, Minimum	300°F	150°C
Low Temperature Flexibility, (90 ° Bend-No flaking or cracking)	-10°F	-23°C
Volatile Organic Content (VOC)	3.24lbs./ U.S gallon	400 grams/ liter

Accelerated Corrosion Tests:

5% Salt Spray (Hours)		
(A) *ASTM B-117 @ 1.3 mils, (2×4×1/8 in. Polished Steel Panels)	2000	-
(B) **DIN 50021 @ 32.5 microns, (125×200mm. DIN 1623 Panels)	-	2500

**ASTM (American Society for Testing and Materials)

* DIN (Deutsche Industrie Normen)

Benefits

Easy Application

TECTYL 506 is formulated for easy application by spray, dip or brush.

Low Cost Protection

TECTYL 506 is a one-coat rust preventive. The thin film provides high coverage and low cost protection.

Long Term Protection

TECTYL 506 provides outstanding external protection of machinery, machinery, machine rolls, machine tools, automotive parts, dies, tubing, and spare parts. TECTYL 506 has a dielectric (insulating) strength of approximately 1000 volts per dry mil of film thickness and therefore protects electrical connections and helps prevent galvanic corrosion.

Surface Preparation

The maximum performance of TECTYL 506 can only be achieved when the metal surfaces, to be protected, are clean and dry. Remove dirt, rust, scaling paint and other contaminants before applying 506.

Application

Ensure Uniform consistency prior to use. Continuous stirring or thinning is generally not required. If product thickens due to cold storage or loss of solvent during use, add only aliphatic mineral spirits and only if necessary to restore consistency. Do not apply heat; fire or explosion may result. Apply at 50-95°F(10-35°C) by spray, dip or brush.

Coverage

The theoretical coverage is 630 sq. ft./gallon(15.4 sq. meters/liter) at the recommended dry film thickness of 1.3 mils (32.5 microns). Material losses during application will vary and must be considered when estimating job requirements.

Removal

TECTYL 506 can be removed with mineral spirits or any similar petroleum solvent, vapor degreasing. TECTYL 506 can be removed from fabrics by normal dry cleaning procedures. Avoid using chlorinated or highly aromatic solvents when removing from painted surfaces as these solvents may adversely affect paint.

Caution: Combustible

TECTYL 506 cures by solvent evaporation. Keep away from heat, sparks and open flames. Use with adequate ventilation. If applied to the interior of an enclosed vessel adequate ventilation is required for cure and to ensure against formation of an explosive atmosphere. For further information, consult Hanval Inc.. Refer to Hanval Inc. Material Safety Data Sheet for health and safety instructions.

Examples of Application

Bombardier. Chrysler. Ford Motors. HUNDAI Heavy Industry. DOOSAN Heavy Industry, Mitsubish Heavy Industry etc.

CAUTION: The data, statements and recommendations set forth in this product information sheet are based on testing, research and other development work which has been carefully conducted by us, and we believe such data, statements and recommendations will serve as reliable guidelines. However, this product is subject to numerable uses under varying conditions over which we have no control, and accordingly, we do NOT warrant that this product is suitable for any particular use. Users are advised to test the product in advance to make certain it is suitable for their particular production conditions and particular use or uses.

WARRANTY: Hanval Inc. warrants all products manufactured by it to be free from defects in material and workmanship. HANVAL INC. MAKE NO OTHER WARRANTIES, WHETHER, EXPRESSED OR IMPLIED, WITH RESPECT TO SUCH RPRODUCTS, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE AND IMPLIED WARRANTIES ARISING FROM A COURSE OF DEALING OR USAGE OF TRADE, ARE DISCLAIMED BY HANVAL INC.. All claims hereunder must be made in writing within 30 days after receipt of the products at the buyer's plant and prior to further processing the products or combining them with other materials or products. Hanval Inc. liability, whether under this warranty or in contract, tort, negligence or otherwise, is limited to the return of the net purchase price paid for any products proven defective or, at Hanval Inc. option, to the repair or replacement of said products upon their return, transportation prepaid, to Hanval Inc.. THE REMEDY HEREBY PROVIDED SHALL BE THE EXCLUSIVE AND SOLE REMEDY OF THE BUYER, AND UNDER NO CIRCUMSTANCES SHALL HANVAL INC. BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES, No Hanval Inc. representative or other person is authorized to change this warranty in any way or to assume for Hanval Inc. any other liability in connection with the sale or use of its products.

REFER TO MATERIAL SAFETY DATA SHEET FOR HEALTH AND SAFETY INFORMATION

HV 01/2014 (Supersedes all previous printings)